

# Colorex

## SOLO



### Product description:

Solo 30/90 is a semi-glossy/glossy, urethane alkyd based clear varnish that is resistant to light. It is intended for wooden surfaces that are not to fade in- as well as outdoors, for instance carpentry, doors, panels and thresholds.

The product is specially designed for the stringent requirements when it comes to varnishing wooden boats, over the water-line.

More fields of application are concrete and wooden as well as parquet floors. Also functions for varnishing well cleaned linoleum floors. The varnish is hard and flexible simultaneously.

### TECHNICAL DATA:

Area of application	Out-/indoors
Binder	Urethane alkyd
Volume Solids	39%
Density	0,90 g/cm <sup>3</sup>
Gloss	30 (semi-gloss)
Washability	Yes. > 10 000 cycles
Thinner/Cleaning	White spirit/ Naphtha
Material consumption	6–10 m <sup>2</sup> /L
Temperature at painting	Minimum +5°C
Tools for painting	Pensel, roller och färgspruta
Dust dry	4 h
Re-paintable	12–24 h
Completely dry	48 h
Colour	Clear
Flammability	2b
VOC category	(Cat. A/i): 500 g/l (2010)

# Colorex

## SOLO



### How to use:

#### Pre-painting

Always start by reading the instructions on the label. It is important to be thorough from the beginning. The use of correct tools and a carefully performed base is the foundation for a successful result. Stir well from the bottom before starting to paint. The air and surface temperature is also important for the end result. Do not paint if it is below +5°C.

The surface must be clean, dry and firm. Brush or scrape away loose old paint/varnish. Sand and wash previously painted surfaces with appropriate cleaner and rinse with water. When varnishing concrete, the foundation must be thoroughly hardened. Prime new concrete with Solo, diluted with up to 50% white spirit. Prime new, not earlier treated, wooden floors with Solo diluted with 20% white spirit.

#### Painting

The product is ready to use. Apply with roller, brush or sprayer (after diluting with white spirit). Apply at least twice in thin layers, because if applied thickly, varnish can result in a yellowish surface. To minimize the risk of fibre-raising on the surface – wipe it with warm water and a cloth. Allow to dry and sand lightly with a sand paper (180- 240 grits) and dry thoroughly before first coat of Solo universal varnish.

#### Post-painting

Wipe off the tools thoroughly before cleaning with white spirit. Seal the tin carefully after use and keep out of reach for children. Liquid residues may not be poured down the drain, but be submitted to the local collection point. Protect the environment, like we do.

#### Maintenance

Wipe off the tools thoroughly before cleaning with white spirit. Seal the tin carefully after use and keep out of reach for children. Liquid residues may not be poured down the drain, but be submitted to the local collection point. Protect the environment, we do.